

## ANTILEAK 7150 Asbestos Rubber Gasket for low pressure

### Technical Data:

Item	Unit	Value
Tensile strength	MPa	$\geq 5.0$
Aging coefficient	%	$\geq 0.9$
Burning loss	%	$\leq 30$
Density	g/cm <sup>3</sup>	1.6- 2.0
Compressibility	%	7~17
Recovery	/	$\geq 35$
Stress relaxation	%	$\leq 50$
Air-tightness	with the temperature of 140-150℃ and the pressure of 1.5-2 MPa, Keep for 30 min without puncture.	

### Available dimensions:

Width and length: 1550mm\*4100mm; 1500mm\*4600mm; 1300mm\*3810mm

Thickness: 0.5mm~5.0mm

Tolerance:  $\pm 0.05$ mm for thickness 0.5mm~1.0mm;  $\pm 0.07$ mm for thickness 2.0mm;  $\pm 0.08$ mm for thickness 3.0mm;  $\pm 50$ mm for width & length.

Special spec. can be required by customers. Special technical requirement can be customized.