

ANTILEAK 7250 Asbestos Rubber Gasket for low pressure

Technical Data:

| Item | Unit | Value |
|-------------------|---|------------|
| Tensile strength | MPa | ≥ 6.0 |
| Aging coefficient | % | ≥ 0.9 |
| Burning loss | % | ≤ 30 |
| Density | g/cm ³ | 1.6- 2.0 |
| Compressibility | % | 7~17 |
| Recovery | / | ≥ 35 |
| Stress relaxation | % | ≤ 50 |
| Air-tightness | with the temperature of 200-220 °C and the pressure of 2-3 MPa, Keep for 30 min without puncture. | |

Available dimensions:

Width and length: 1550mm*4100mm; 1500mm*4600mm; 1300mm*3810mm

Thickness: 0.5mm~5.0mm

Tolerance: ± 0.05 mm for thickness 0.5mm~1.0mm; ± 0.07 mm for thickness 2.0mm; ± 0.08 mm for thickness 3.0mm; ± 50 mm for width & length.

Special spec. can be required by customers. Special technical requirement can be customized.