

ANTILEAK 7350 Asbestos Rubber Gasket for medium pressure

Technical Data:

Item	Unit	Value
Tensile strength	MPa	≥ 9.0
Aging coefficient	%	≥ 0.9
Burning loss	%	≤ 30
Density	g/cm ³	1.6- 2.0
Compressibility	%	7~17
Recovery	/	≥ 40
Stress relaxation	%	≤ 50
Air-tightness	with the temperature of 290-300℃ and the pressure of 4-5 MPa, Keep for 30 min without puncture.	

Available dimensions:

Width and length: 1550mm*4100mm; 1500mm*4600mm; 1300mm*3810mm

Thickness: 0.5mm~5.0mm

Tolerance: ± 0.05 mm for thickness 0.5mm~1.0mm; ± 0.07 mm for thickness 2.0mm; ± 0.08 mm for thickness 3.0mm; ± 50 mm for width & length.

Special spec. can be required by customers. Special technical requirement can be customized.