

ANTILEAK 9200 Non-asbestos Gasket for common use

Technical data:

| Item | Unit | Value |
|---|-------------------|-------------------|
| Color | / | / |
| Density | g/cm ³ | 1.85~1.92 |
| Tensile strength (ASTMF-152) | MPa | ≥7.0 |
| Compressibility (ASTMF-36) | % | 6~13 |
| Recovery (ASTMF-36) | % | ≤35 |
| Creep relaxation rate | N/mm ² | ≤40 |
| Sealability (ASTMF-37) | ml/min | ≤1.0 |
| Oil resistance Thickness increase in ASTM 3# oil (ASTMF-146) | % | ≤12 |
| Temperature | °C(°F) | 200~250 (392~482) |

Available dimensions:

Width and length: 1270mm*3810mm; 1500mm*2000mm; 1500mm*1500mm

Thickness: 0.4mm~5mm

Tolerance: thickness ±10%; width & length ±50mm

Special spec. can be required by customers. Special technical requirement can be customized.