

## ANTILEAK 9250 F Non-asbestos Gasket with excellent air-tightness

### Technical data:

Item	Unit	Value
Color	/	/
Density	g/cm <sup>3</sup>	1.75~1.90
Tensile strength (ASTMF-152)	MPa	≥8.0
Compressibility (ASTMF-36)	%	7~17
Recovery (ASTMF-36)	%	≥50
Creep relaxation rate	N/mm <sup>2</sup>	≤40
Sealability (ASTMF-37)	ml/min	≤0.1
Oil resistance Thickness increase in ASTM 3# oil (ASTMF-146)	%	≤10
Temperature	°C(°F)	200~250 (392~482)

### Available dimensions:

Width and length: 1270mm\*3810mm; 1500mm\*2000mm; 1500mm\*1500mm

Thickness: 0.4mm~5mm

Tolerance: thickness ±10%; width & length ±50mm

Special spec. can be required by customers. Special technical requirement can be customized.