

Technical Data of Asbestos Packing

Antileak Model No.	Product Name	Construction	Service Range		
			Max. Temperature	Max. Pressure	Max. Velocity
2900	Dusted Asbestos Packing	Braided from dusted asbestos yarn	<300°C	2MPa	4 meters/sec
2900 T	Dust free Asbestos Packing	Braided from dust free asbestos yarn	<300°C	2MPa	4 meters/sec
2900 G	Graphite Asbestos Packing	Braided from asbestos yarn that treated with graphite	<350°C	3MPa	4 meters/sec
2900 WG	Graphite Asbestos Packing reinforced with wire	2900 G reinforced with wire	<500°C	10MPa	2 meters/sec
2900 R	Rubber Asbestos Packing	Braided from asbestos yarn that treated with rubber liquid	<250°C	2MPa	3 meters/sec
2900 WR	Rubber Asbestos Packing reinforced with wire	2900 R reinforced with wire	<400°C	2MPa	4 meters/sec
2900 P	Asbestos Packing with PTFE impregnation	Braided from asbestos yarn and impregnated with PTFE	<280°C	2MPa	8 meters/sec